

LUMINANCE SAFETY

ENERGY-SAVING FILM



BENEFITS

- Rejects up to 64% of solar energy, reducing energy costs, heat build-up, and glare
- Blocks up to 99.9% of ultraviolet rays, helping to protect furnishings by reducing premature fading
- Helps hold shattered glass together should a break occur
- Helps slow down entry through glass
- Blue-gray hue with low interior and high exterior reflectivity
- Reduces glare and eye fatigue
- Optically-clear sputtered film with advanced color stable technology
- Manufacturer's warranty*

RECOMMENDED APPLICATIONS

- Schools and Universities
- Public Buildings
- Health Care Facilities
- Commercial Offices
- Hotels
- Homes



* Ask your dealer about warranty details.

LUMINANCE SAFETY

ENERGY-SAVING SAFETY FILM



GLASS TYPE	RESIDENTIAL 1/8" (3 mm)		COMMERCIAL 1/4" (6 mm)	
	SINGLE PANE CLEAR	DUAL PANE CLEAR	SINGLE PANE CLEAR	DUAL PANE CLEAR
Visible Light Transmittance	27%	24%	25%	23%
Total Solar Energy Rejected	64%	57%	67%	57%
Solar Heat Gain Coefficient	0.36	0.43	0.33	0.43
Winter Median U-Value	1.03	0.47	0.99	0.47
Glare Reduction	70%	70%	72%	71%
Ultraviolet Rejected	99.9%	99.9%	99.9%	99.9%
Total Solar Transmittance	22%	17%	17%	14%
Total Solar Reflectance	31%	32%	29%	25%
Total Solar Absorptance	47%	51%	54%	61%
Visible Light Reflectance: Exterior	32%	39%	35%	36%
Visible Light Reflectance: Interior	22%	23%	22%	23%
Shading Coefficient	0.42	0.50	0.39	0.50
Emissivity	0.81	0.78	0.78	0.78
Light to Solar Heat Gain Ratio	0.75	0.56	0.76	0.53
Summer Solar Heat Gain Reduction	58%	43%	59%	38%
Winter Heat Loss Reduction	0%	2%	4%	0%

DESIGNED TO SAVE ENERGY, REDUCE GLARE, AND REJECT UV RAYS WHILE MAINTAINING EXTERIOR VIEWS

Dual-Reflective films offer superior energy savings through lower interior reflectivity and higher exterior reflectivity allowing for excellent views to the outside both day and night. These films have a blue-gray appearance and are traditionally installed on commercial buildings, but have popularity in homes in regions with high levels of sunlight.

All solar properties have been measured in accordance with NFRC standards. All values averaged from routinely accumulated quality control data.